



ROTARY KIILN BAUXITTE

Calcined Rotary Kiln Bauxite

Calcined Bauxite is one of the hardest natural minerals after diamond.

Chemical Analysis	%	Physical Data	
Al ₂ O ₃	75-90	Shape	Angular
TiO ₂	2-3	LOI	0.1-0.5%
SiO ₂	6-18	Specific Gavity g/cm ³	3.70
Fe ₂ O ₃	0.5-2.5	Bulk Density g/cm ³	2.90-3.25
P ₂ O ₅	0-0.3	Hardness Mohs	9.0
MgO	0-0.2	Moisture Content	0.1-0.3
CaO	0-0.4	Polished Stone Value	70Min
CaO	0-0.4	Aggregate Abrasion Value	10Max

Regular Particel Sizes

0-1mm, 1-3mm, 3-5mm, 5-8mm,...

HS Code

260600

Packing

1.0MT - 1.5MT big jumbo bag.

SEPPE TECHNOLOGIES

Believe In Good Materials!

Contact Us

Mobile

+86 185 3023 9533

Website

www.seppe.cn

Phone

+86 373 380 6139

Email

Info@seppe.cn

More Details, Ask SEPPE Now!